

Falcon Power Global

For Safety Equipment



فالكون باور العالمية

لأجهزة السلامة



Falcon Gold
FIRE RATED DOOR



0547777503

Info@falconpower.sa
www.falconpower.sa

6112 Palestine St. Jeddah 23341
KINGDOM OF SAUDI ARABIA



فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold

**MATERIAL SUBMITTAL
FOR
FIRE RATED DOOR**



Falcon Gold

Index

Door Data Sheet.

Fire Test Certificate (Intertek Approval).

Door Accessories Data Sheets and Certificate.

1– Honeycomb.

2– Anchor.

3– Powder Coating.

4– Vision Glass.

5– Mill Test Report.

Civil Defence.

Company Licence.

Quality Plan.

ISO Certificate.

Draft Wrranty.



فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold

Door Data Sheet.



Project Name :

FORT Fire Steel doors Specification

SR. NO	DESCRIPTION	PROPOSED SPECIFICATION
1	Brand Name	Fort
2	Door and Frame Fire Resistance Standard	BS476 Part22(1987)/EN1634-1(2014)
3	Leaf Sheet Thickness	1mm
4	Leaf Thickness	45mm
5	Door Core	Honeycomb
6	Door Edges	Seamed
7	Door Finish Paint	Polyester powder coating
8	Frame Sheet Thickness	1.2mm
9	Frame Jamb Depth	150mm
10	Frame Construction	Welded
11	Frame Profile	Single rabbet
12	Door Fire Rating	Up to 120 Minutes
13	Vision Panel	-



PRODUCTS

Bin Ghurair Trading is proud to be able to offer the supply and installation of many door products than ever before. Following is the list of our main Products.

Steel doors and Frames

- **Fire rated hollow metal steel door & frame**
 - I. UL 10B/10C: 90 Min Fire rating
 - II. BS476: Part 22 (1987) from BRE (UK) for 180Min FR
 - III. BS476: Part 22 (1987) from Exova Warrington for 240Min FR
- **Non Fire rated hollow metal steel door & frame**
- **Special Door types from branded Supplier.**
 - I. Acoustic door (STC-30,STC-32,STC-37)
 - II. Temperature Rise Rated doors (TRR doors)
 - III. Smoke Proof Doors

Builder's hardware (ironmongery)

- I. North American Hardware.
- II. European Hardware



BGT Hard Wares

Door Handles, Locks & Hinges

BGT's line of mortise, Handles available in a broad array of metal, designs, finishes, sizes, and weights and cylindrical, tubular, and dead bolt locks offers a comprehensive selection locks that meet the functional and aesthetic requirements of commercial and institutional doors.

BGT offers the broadest range of full mortise hinges in a variety of metals, finishes, sizes, and weights to meet all your load bearing and security applications. They include two, three, and five knuckle styles, swing clear hinges, wide throw hinges, anchor hinges, electric hinges, institutional hinges and pivots.






Nomenclature for standard FORT® door designs.

FORT® door Designs are in accordance with ANSI A250.7-1997 "Nomenclature for standard steel doors & Steel frames" and 'SDI 106-99 'Recommend Standard door type Nomenclature'.

NOMENCLATURE FOR STANDARD DOOR DESIGNS



NOMENCLATURE LETTER SYMBOLS EXPLANATORY NOTES

- F. 'Flush door'
- V. "Vision Lite Door", 250mm Square-lite.
- N. 'Narrow Lite Door', near the lock stile.
- G. 'Glass Door'
- L. "Louvered door" Fire rated & Non_Fire rated
- FL. "Full Louvered Door"
- D. 'Dutch Door', A two panel door, separated horizontally





FORT® Doors are available with many features

- ✓ Non-Handed
- ✓ Handed
- ✓ Seamed edge
- ✓ Seam edge track welded and filled
- ✓ Polystyrene core doors - NFR
- ✓ Honeycomb core doors - BS476 from Exova Warrington for 240Min FR
- ✓ Polyurethane core doors - NFR
- ✓ Rock wool, Steel stiffened core doors - UL 10B/10C: 90 Min Fire rating
- ✓ Steel Stiffened with any option of core
- ✓ Oversize doors and frames
- ✓ Double acting doors - NFR
- ✓ Transom panels
- ✓ Vertical or horizontal removable or non removable mullions
- ✓ Bi-fold doors
- ✓ Custom size doors
- ✓ Louver doors
- ✓ Doors with variety of vision panels in various sizes and shapes
- ✓ Pocket pivot preparations
- ✓ Concealed hardware preparation
- ✓ Mortise / Cylindrical lock preparation etc.
- ✓ Security Doors



BGT Service after sale,

Due to our commitment to provide all our clients with top class service, we established BGT Maintenance Division to attend all service inquiry for all our existing installations in U.A.E.

We have invested in this Dept. to ensure high level of concern to attend all our client service calls within 48 hours policy and to become effective on practical performance of our service teams.

Our Features:

Mobile equipped service vans which is able to perform all your door required maintenance

Our Toll free service to attend all your call at any time of the day.

4 service teams trained to solve all door problems within 2 hours.

BGT Maintenance work through two types of plans:

- I. Annual Service Maintenance Contract for our client by attending 3 visits yearly with some standard replacement items to ensure the door excellent performance & longer lifetime.

Attend on call within 48 hours, means our Team will come to visit once he receive the call within 48 hours and charge on site.





فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold

Fire Test Certificate (Intertek Approval).

Certificate of Compliance



This is a certificate of compliance to certify that the bearer has successfully completed the requirements of the above scheme which include the testing of products, the initial assessment, and are subject to continuing annual assessments of their compliance and testing of samples of products taken from production (as applicable to the scheme) and has been registered within the scheme for the products detailed.

You have been awarded:

WH Service Mark 2014 for Category D - Door/frame Assemblies

Standards: BS 476 Part 22 (1987)

Certificate number: WH18-29215809

Organization: Bin Ghurair Metal Industries L.L.C.

Plot No. 597-400

Dubai Investment Park 2

Dubai

United Arab Emirates

Product: Bin Ghurair - BS 476 Part 22 - Swinging Type Fire Door & Frame Assembly (Honeycomb Infill)

Spec ID: 43264

Fire Rating: 2 Hour Fire Rated, 4 Hour Fire Rated

Label Traceability: W/N 21535


Listing Information: See following page(s)

Certification body: Intertek Testing Services NA, Inc.

Initial registration: April 16, 2018

Date of expiry: December 31, 2023

Issue status: 8

Authorized By: 
Jean-Philippe Kayl, Director of Certification

Intertek Testing Services NA, Inc.
545 E. Algonquin Road, Ste H., Arlington Heights, IL 60005 USA
Phone: 847-439-5667 Fax: 847-439-7320

www.intertek.com

The certificate and schedule are held in force by regular annual surveillance visits by Intertek Testing Services NA, Inc. and the reader or user should contact Intertek to validate its status. This certificate remains the property of Intertek Testing Services NA, Inc. and must be returned to them on demand. This Certificate is for the exclusive use of Intertek's Client and is provided pursuant to the Certification agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this certificate. Only the Client is authorized to permit copying or distribution of this certificate and then only in its entirety. Use of Intertek's Certification mark is restricted to the conditions laid out in the agreement. Any further use of the Intertek name for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. Initial Factory Assessments and Follow up Services are for the purpose of assuring appropriate usage of the Certification mark in accordance with the agreement, they are not for the purposes of production quality control and do not relieve the Client of their obligations in this respect.

LISTING INFORMATION

FIRE RESISTANT PRODUCT AND COMPONENTS

Fire door and frame assembly - Honeycomb infill type

PRODUCT COVERED

Single and Double Leaf Steel Fire Door and Frame

PRODUCT DESCRIPTION

Single and Double leaf (1mm thick), hollow metal type, honeycomb infill fire doors intended for use in masonry constructions.

The door frame (1.2mm thick) can be installed with or without grouting.

Limitations:

Minimum latch throw - 12mm.

Maximum sizes for Single leaf door assembly:

For 240 minutes rating (as tested):

Single door frame - 976mm x 2200mm x 146mm (w x h x jamb depth)

Single door leaf - 870mm x 2132mm x 45mm (w x h x thickness)

Allowed Extended Sizes for **120 minutes or lower** fire rating:

	Width (mm) (30%)	Height (mm) (30%)	Area (sq. m) (35%)
Single Door Frame	1268 (at 2285mm height)	2860 (at 1014mm width)	2.90
Single Door Leaf	1131 (at 2214mm height)	2772 (at 903mm width)	2.50

Allowed Extended Sizes for **180 minutes** fire rating:

	Width (mm) (20%)	Height (mm) (20%)	Area (sq. m) (25%)
Single Door Frame	1171 (at 2292mm height)	2640 (at 1017mm width)	2.68
Single Door Leaf	1044 (at 2221mm height)	2558 (at 906mm width)	2.32

Maximum sizes for Double leaf door assembly:

For 240 minutes rating: Double leaf door assembly not allowed for 240 minutes fire rating

For 120 minutes rating:

Maximum Double door frame size: 1952mm x 2200mm x 146mm (w x h x jamb depth)

Maximum Double door leaf size (each leaf): 870mm x 2132mm x 45mm (w x h x thickness)

Allowed Extended Sizes for **60 minutes or lower** fire rating:

	Width (mm) (20%)	Height (mm) (20%)	Area (sq. m) (25%)
Double Door Frame	2342 (at 2292mm height)	2640 (at 2033mm width)	5.37
Double Door Leaf	1044 (at 2221mm height)	2558 (at 906mm width)	2.32

Allowed Extended Sizes for **90 minutes** fire rating:

	Width (mm) (15%)	Height (mm) (15%)	Area (sq. m) (20%)
Double Door Frame	2244 (at 2296mm height)	2530 (at 2037mm width)	5.15
Double Door Leaf	1000 (at 2225mm height)	2452 (at 908mm width)	2.23

Allowed vision panel glass size - 225mm x 725mm x 5mm (w x h x thickness)

RATINGS

The single & double door and frame assembly has been evaluated in accordance with BS 476 Part 22 standards and achieved the following ratings:

Integrity	120 Minutes
-----------	-------------

Note: Single door assemblies are allowed for up to 240 Minutes Integrity Classification period



فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold

Door Accessories Data Sheet.



فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold



Located in the garden city of India, Bangalore, HonECORE™ is the largest selling premium paper honeycomb brand in India with a state of the art facility to manufacture paper honeycomb with highly advanced paper honeycomb production technology.

HonECORE™, today stands as a well renowned and the most recognized brand of paper honeycomb made in India and has, under its portfolio of client's, some of the distinguished players from the wood working, sheet metal and packaging industry.



Complete range of paper honeycomb solutions through a single window approach with its strategic collaboration with



HonECORE™ provides end-to-end paper honeycomb solutions under one roof. Made from recycled kraft paper honECORE is 100 % Eco-Friendly, Borer and Termite free.



Distinct Cost Advantages of using honECORE-Paper Honeycomb

Transportation Raw Material:

Particulars	Capacity	No of Doors that can be mfr.
1 truck 22'	16 tons	355 nos
1 truck 22'	16tons	9000 nos

Transportation of finished products:

Particulars	Capacity	No of doors
1 Truck 22' Wood	16 tons	355
1 Truck 22' Honecore Doors	16tons	630

Inventory Storage:

- 1 sqm pallet of honECORE can hold 500 doors material.
- You need 1375 cubic ft of space for the similar quantity of doors.



Faster Production Times:

- Time taken to manufacture 1 wooden door the time taken against Honeycomb Doors.

Process Involved	Wooden Doors	Honeycomb Doors
Frame Assembly	2 mins	2 mins
Core Assemble	8 mins	1 min
Process Assembly	4 mins	2 mins
Pressing	7 mins	6 mins
Total Time Taken	21 mins	11 mins

SUMMARY OF DISTINCT COST SAVING ADVANTAGES BY USING HONECORE™

- You get 25 times more material at the same logistic cost
- You save up to 50 % of transportation of finished honeycomb doors as compared to wooden doors.
- You save 90 % of inventory space
- 50 % faster production times saving 50 % of work force.



HonECORE™-Technical Data Sheet

Product Code	honECORE 1500/15	honECORE 1500/21	honECORE 1800/28
Cell Size	15mm	21mm	28mm
Maximum Width(expanded)	Up to 1200 mm	Up to 1200 mm	Up to 1200 mm
Length	As per client specification	As per client specification	As per client specification
Thickness	6mm-500mm	6mm-500mm	6mm-500mm
Paper	150 gsm Recycled Kraft	150 gsm Recycled Kraft	180 gsm Recycled Kraft
Density	30 kg/m ³	22kg/m ³	18kg/m ³
Compression Strength(@3% moisture content)	3.5 kg/cm ²	1.75kg/cm ²	1.95kg/cm ²
Moisture Content(ex-works)	5-7 %	5-7%	5-7%

Product Specification	
Block Cut honECORE	Standard Size (width* length) honECORE 1500/15 – 915mm*2150mm honECORE 1500/21 - 915mm*2150mm honECORE 1800/28 – 1015mm*2150mm
Continuous honECORE	Width upto 1200mm(expanded) and length specified by client.
Minimum Order Quantity	1000 sqm.
honECORE EX/1500/D	Recommended for Continuous honECORE.

Annexure:

1. Paper used is 100 % Eco-Friendly.
2. honECORE™ is 100 % Anti-Fungi, Borer and Termite Free
3. Greater compression strengths can be achieved by using honECORE expander EX/1500/D. The expander would further bring the moisture content of the paper below 3 %.



To achieve the most optimum compression values for a given specification of paper honeycomb, the moisture level's need to be to the minimum level possible.

Introducing honECORE™ EX/1500/D expander series.

The honECORE™ EX/1500/D expander series are the state of the art and technologically most advanced paper honeycomb expander machines complimenting the usage of honECORE™-Paper Honeycomb Solutions. The core comes in a continuous format which is fed through electric heating which in a controllable temperature ranging from 80-150 Degree Celsius expands remove's the moisture content from the paper to 2-3 % . By this, the paper comes out in a expanded format which in turn bear's maximum compression value for a given surface area. This through an in built PLC controlled cutter is cut to desired lengths ready for production.

The advantage of using the honECORE™ expander machine are:

Optimum utilization of the raw material:

Our client saves 20-25 % of the material as the honeycomb core is expanded and cut to sizes as against using the material manually.

Achieve maximum compressive strength as the moisture content of the material is brought down to 2-3 % before production.

Faster production times:

Up to 4m/min (2 doors/min) speed's can be achieved through honECORE EX/1500/D. Since the honeycomb is cut to size and adequately expanded (does not contract back as against using it manually), it increases production capabilities substantially.

Saving of work force:

Our client's save 2 workmen which would be required when one manually expands the honeycomb core. Hence, we at team honECORE™ strongly recommend to our client's to procure the expander machine to get the best compression results and optimum utilization of the material i.e., achieve greater product quality and efficiency.




Particulars	Specifications
Motor power	0.2KW
Heating type	Electric heating
Total power for heating device	12 KW
Production speed (max)	4m/min
Applicable core paper width (Max)	1500mm
Expanded core paper width(Max)	1200mm
Thickness for core paper	10-90 mm
Dimension of machine	4200*1800*1300mm
Cutting Type	Automatic Cutting.

Model Number: honECORE™ Ex/1500/D





HonECORE™ Applications:

SEMIFINISHED PANELS													
Overview of all facts:													
	<p>Design of lightweight panels Lightweight panels consist of three base elements:</p> <ul style="list-style-type: none"> • Top layer: top side and bottom side <ol style="list-style-type: none"> a. 3 mm, 4 mm MDF, HDF b. 3 mm, 4 mm Moisture resistant ply c. 4 mm ,8 mm Particle board • Core: Hexagonal Paper Honeycomb • Frame: optional (with or without) 												
	<p>Characteristic of lightweight panels Lightweight panels provide excellent characteristics for furniture construction and shop fitting.</p> <table border="0"> <tr> <td>Weight reduction</td> <td>Very high load capacity</td> </tr> <tr> <td>High stability</td> <td>Long service life</td> </tr> <tr> <td>Wide spans</td> <td>Almost no sagging</td> </tr> <tr> <td>Optimized transport</td> <td>Easy assembly</td> </tr> <tr> <td>Eco friendly</td> <td></td> </tr> <tr> <td colspan="2">Aesthetic appeal using thicker panels</td> </tr> </table>	Weight reduction	Very high load capacity	High stability	Long service life	Wide spans	Almost no sagging	Optimized transport	Easy assembly	Eco friendly		Aesthetic appeal using thicker panels	
Weight reduction	Very high load capacity												
High stability	Long service life												
Wide spans	Almost no sagging												
Optimized transport	Easy assembly												
Eco friendly													
Aesthetic appeal using thicker panels													
	<p>Use of lightweight panels The lightweight panels are suitable for a wide variety of applications in kitchens, living rooms and bedrooms. For example:</p> <table border="0"> <tr> <td>Home furniture</td> <td>Conference tables</td> </tr> <tr> <td>Kitchen worktops</td> <td>Shelving</td> </tr> <tr> <td>Desks</td> <td>Shop fitting</td> </tr> <tr> <td>Doors</td> <td>Partitions</td> </tr> </table>	Home furniture	Conference tables	Kitchen worktops	Shelving	Desks	Shop fitting	Doors	Partitions				
Home furniture	Conference tables												
Kitchen worktops	Shelving												
Desks	Shop fitting												
Doors	Partitions												



In construction:

- Doors (wooden, metal, frp etc)
- Panels – table top, kitchen cabinetry, flat panel modular furniture (ranging from 12mm up to 150mm thick panels and more)
- Clean Rooms/Panels
- False roofing, ceiling
- Office and Residential Interiors.
- Pin up boards, white boards.

In Packaging:

- Paper Pallets
- Void Fillers
- Separators
- Customised primary and secondary packaging.

HonECORE™, is an evolutionary product that replaces non eco-friendly materials like wood and EPS in their respective applications while preserving the key virtues of their usage in the concerned applications. On its own HonECORE™ is an eco-friendly, versatile, flexible and lightweight material that has excellent compatibility with other materials and an excellent strength-to-weight ratio. It combines with plywood, steel, plastics, FRP and many other materials as its sandwich faces to form some of the strongest composite panels for its weight and dimensions. It is also more economical than most materials, thereby making it an ideal choice. As a product made from recycled paper and eco-friendly glue, it is a boon to the earth as a 100% bio-degradable, non polluting, eco-friendly material. Large scale usage of paper honeycomb can drastically boost a country's aim of preserving the nature.

So the change is visible.

The change is not the technology..

It is our "acceptance of the technology"

A technology which is lightweight, eco-friendly, sustainable and provides economy of operations.

It is time we accept the change..

It is time we "Get Wise"!

Join us .. it's the Green Revolution!

Thanking you,
Yours faithfully,
For Lsquare Eco-Product's Pvt Ltd,

Rohit Bhandari
(Business Development)



METAL FRAM ANCHOR ZINC PLATED



Art.No. 1904 41072

Head configuration :	Countersunk, Flat head
Environmental conditions:	Indoor, dry conditions
Type of fastening :	Through-fastening
Material composition:	Steel, 4.6 grade, zinc-plated (min. 5 µm), Sheet steel, sendzimir zinc-plated to approx. 1.6µm
Installation direction :	All
Material, corrosion :	Steel, zinc-plated

Anchor Size	Drill (φ)	Sleeve length (L)	Machine Screw	Drill Hole Depth	Fixing Length Max	Article No.	Item Name
φ10x172	10	72	M6x85	50	40	1904 41072	Metal Fram Anchor Zinc Plated 10*72
φ10x92	10	92	M6x105	50	60	1904 41092	Metal Fram Anchor Zinc Plated 10*92

Product Data Sheet

AkzoNobel Powder Coatings

Interpon D1025 Texture

Product Code

JP437W

Product Description

Interpon D1025 Texture (or Sandpaper, or Sablé), is a range of powder coatings with texture aspect, intended for use on architectural aluminium and galvanized steel. specifically formulated with TGIC.

Interpon D1025 Texture has a better scratch resistance than many conventional systems.

As part of the Interpon D1025 series of architectural coatings, **Interpon D1025 Texture** gives excellent exterior durability and colour retention and conforms to the requirements of all the major architectural standards. All **Interpon D1025 Texture** are lead-free and meet the requirements of Qualicoat class 1, EN12206, and EN13438 (formerly BS6496 & BS6497), - as well as AAMA 2603-13.

Qualicoat License Number: P-1348 (UAE)

Metallic colours approved: Yes

Powder Properties

Chemical type	Polyester
Gloss (EN ISO 2813 (at 60°))	Texture
Particle size	Suitable for electrostatic spray
Specific gravity	1.2 – 1.9 g/cm ³ depending on colour
Storage	Dry cool conditions below 30°C (<i>open boxes must be resealed</i>)
Shelf life	24 months below 30°C
Stoving schedule (Object Temperature)	15-30 minutes at 190°C 10-20 minutes at 200°C 8-16 minutes at 210°C Test condition: 10 minutes at 200°C

Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

Substrate	Aluminium (0.5-0.8 mm Al Mg1)
Pretreatment	Chromate (DIN 50539)
Application method	Electrostatic spray
Dry Film Thickness	70 – 120 microns (as per the pattern size)
Stoving Schedule	10 minutes at 200°C (object temperature)

Mechanical Tests

Flexibility	ISO1519 (cylindrical mandrel)	Pass 5mm
Adhesion	ISO2409 (2mm crosshatch)	Gt0
Erichsen Cupping	ISO1520	Pass 5mm
Impact	ISO6272:1993	Pass 2.5 Joules reverse & direct (20 in lb)
Buchholz hardness	ISO2815	>80

Chemical Tests

Acetic acid salt spray	ISO9227	<16 mm ² corrosion/10cm, 1000 hours
Constant humidity	ISO6260	No blistering, creep <1mm (1000 hours)
Sulphur Dioxide	ISO3231	Pass 30 cycles – no blistering, gloss loss or discoloration
Permeability	EN12206-5.10	Pressure Cooker – pass 1 hour no blistering

Interpon D1025 Texture

Chemical Resistance		Generally good resistance to acid, alkalis and oil at normal temperatures
Mortar Resistance	EN12206-1	No effect after 24 hours
Exterior durability	ISO2810 (1 year)	>50% gloss retention Colour retention according to GSB standard/Qualicoat class 1 Chalking noe in excess of minimum in ASTM D659:1980
Accelerated Weathering	ISO 11341 (1000 hrs) QUV B 313 (300 hrs)	Gloss retention \geq 50% Gloss retention \geq 50%

Pretreatment

For maximum protection it is essential to pretreat components prior to the application of **Interpon D1025 Texture**.

Aluminium components should receive a full multi-stage chromate conversion coating or suitable chrome-free pre-treatment or suitable pre-anodising to clean and condition the substrate. Detailed advice should be sought from the pre-treatment supplier.

Galvanised steel requires surface preparation by either multi-stage pretreatment using either zinc phosphate or chromate conversion or controlled sweep blasting. Depending on the type of galvanizing, degassing or use of anti-bubbling additives may be required – follow the procedural advice of the pretreatment supplier.

Interpon D1025 Texture products may also be used on cast or mild steel. For outdoor use, **Interpon PZ** anti-corrosive primer over a correctly prepared substrate is recommended.

Application

Interpon D1025 Texture powders can be applied by manual or automatic electrostatic spray or tribo-charging equipment. For solid shades, unused powder can be reclaimed up to a maximum of 20% using suitable equipment and recycled through the system. Please consult AkzoNobel for further details as to the correct mixing ratio for virgin/reclaim powder.

All powders can show small colour differences from batch to batch, this is normal and unavoidable. While AkzoNobel take every precaution to minimize visible differences, this cannot be guaranteed. Applicators and fabricators are advised to use a single batch for parts that will be assembled together. Differences are more likely with special effect powders.

Bonded products have better application properties than blended products (more stable) but attention should still be paid to line settings in order to avoid "marble effect" and changes in aspect after recycling. For more details it is suggested to read the *Metallic Application Guideline*.

Different substrates (aluminium, steel, galvanized steel...), use of primer, and big changes in film thickness may give a different aspect.

Products with different codes should not be mixed even if same colour and gloss.

Post Application

For specific advice on the suitability of post coating processes such as bending or the use of sealants, adhesives, thermal break, cleaning etc, please consult AkzoNobel.

Maintenance

For specific advice on Cleaning and Maintenance, please consult the Interpon D series *Cleaning and Maintenance Guidelines* available from AkzoNobel.

Safety Precautions

Please consult the Material Safety Datasheet (MSDS) available from AkzoNobel.

Interpon D1025 Texture

Disclaimer

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Akzo Nobel UAE Paints L.L.C.
Al Quoz Industrial Area 1
Street No. 8
Dubai
United Arab Emirates

T +971 (0) 43472491
F +971 (0) 43472339

For more information, contact your
local AkzoNobel representative
www.interpon.com/contact-us

Copyright © 2015 Akzo Nobel Powder Coatings Ltd. Interpon is a registered trademark of AkzoNobel
Interpon D1025 Texture- Issue 15
Issued: 20/12/2016

Interpon

APPROVAL

for coating materials

The Association for Quality Controls in the Lacquering, Painting and Coating Industry, abbreviated to QUALICOAT, hereby grants an approval based on the test results

Report submitted by (Testing laboratory):	IFO GmbH, Institut für Oberflächentechnik
Date of issue of the Approval:	03.05.2016
Approval valid until:	31.12.2017
System name:	Interpon D2525 fine texture
Valid only for Sublimation:	No
Gloss Category:	1
Class:	2
Structured Finished:	Yes (Textured)
Extension for P/P:	No
Extension for sublimation:	No
Metallic colours approved:	Yes
Banned colours:	-
Manufactured by the company:	Akzo Nobel UAE Paints L.L.C.
Place:	AE - Dubai
P-No:	P-1349

This product may be described and labelled as follows

Product tested and approved for the quality mark



and may therefore be offered to all companies holding the quality label for paint, lacquer and powder coatings on aluminium for architectural applications

Zurich, 1 January 2017

QUALICOAT

M. C. Panam

Mohammed C. Panam
President

Josef Schoppig

Josef Schoppig
General Secretary

QUALICOAT, P.O. Box 1507, CH-8027 Zurich - Tödistrasse 47, 80027 Zurich (Switzerland)
Phone: ++41 43 305 09 70/79 - Fax: ++41 43 305 09 98 - E-Mail: info@qualicoat.net - Internet: www.qualicoat.net

APPROVAL

for coating materials

The Association for Quality Controls in the Lacquering, Painting and Coating Industry, abbreviated to QUALICOAT, hereby grants an approval based on the test results

Report submitted by (Testing laboratory):	IFO GmbH, Institut für Oberflächentechnik
Date of issue of the Approval:	14.02.2014
Approval valid until:	31.12.2017
System name:	Interpon D2525 Satin
Valid only for Sublimation:	No
Gloss Category:	2
Class:	2
Structured Finished:	No
Extension for P/P:	No
Extension for sublimation:	No
Metallic colours approved:	Yes
Banned colours:	-
Manufactured by the company:	Akzo Nobel UAE Paints L.L.C.
Place:	AE - Dubai
P-No:	P-1202

This product may be described and labelled as follows

Product tested and approved for the quality mark



and may therefore be offered to all companies holding the quality label for paint, lacquer and powder coatings on aluminium for architectural applications

Zurich, 1 January 2017

QUALICOAT

M. C. Panam

Mohammed C. Panam
President

Josef Schoppig

Josef Schoppig
General Secretary

QUALICOAT, P.O. Box 1507, CH-8027 Zurich - Tödistrasse 47, 80027 Zurich (Switzerland)
Phone: ++41 43 305 09 70/79 - Fax: ++41 43 305 09 98 - E-Mail: info@qualicoat.net - Internet: www.qualicoat.net

TELEPHONE (AREA CODE 214)

865-0593
558-0594
421-1400

CABLE ADDRESS "DALAB"

DALLAS LABORATORIES, INC.

CONSULTANTS AND TECHNOLOGISTS
ANALYTICAL AND RESEARCH CHEMISTS —
CHEMICAL ENGINEERS — PETROLEUM ENGINEERS

P. O. BOX 152837
1323 WALL ST.

DALLAS, TEXAS 75315

MEMBERS

AMERICAN INSTITUTE OF CHEMICAL ENGINEERS
NATIONAL SOCIETY OF PROFESSIONAL ENGINEERS
TEXAS SOCIETY OF PROFESSIONAL ENGINEERS
ASM INTERNATIONAL
SOCIETY OF PETROLEUM ENGINEERS OF AIME

MEMBERS

AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY FOR TESTING MATERIAL
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL

Submitted by: Interpon Powder Coatings
Technical Group Leader - Industrial
4150 East 56th St.
Cleveland, OH 44105

Attn: Bob Rowles

Date: April 13, 2005

Report No.: 36048
P.O. #4500126529

REPORT

Sample:

Coated aluminum extrusions
Paint: Interpon YM 205U
Production Date: Unknown
Cure: 15 minutes @ 400°F
Pre-treatment: Chromate
Drawing: Not Supplied

A. Procedure

Submitted sample was tested for information purpose according to AAMA 2604-02 "Voluntary Specification, Performance Requirements and Test Procedures for High Performance Organic Coatings on Aluminum Extrusions and Panels", Sections 7.1 through 7.8.2, with the following results:

B. Results

<u>Test</u>	<u>Results</u>	<u>AAMA 2604-02 Specification Requirements</u>
7.1 Color Uniformity	Standard	Standard
7.2 Specular Gloss	20.3	As Reported
7.3 Dry Film Hardness	Pass F	F Hardness and No Film Rupture
7.4 Film Adhesion		
7.4.1.1 Dry	Pass	No Removal of Film from Substrate
7.4.1.2 Wet	Pass	No Removal of Film from Substrate
7.4.1.3 Boiling Water	Pass	No Removal of Film from Substrate
7.5 Impact Resistance	Pass	No Removal of Film from Substrate.

THE ANALYSES OF THE ABOVE SAMPLE OR SAMPLES DO NOT IMPLY AN ENDORSEMENT. THIS REPORT, OR ANY PART THEREOF MAY NOT BE REPRODUCED OR USED FOR ADVERTISING PURPOSES WITHOUT OUR EXPRESS WRITTEN CONSENT.


<u>Test</u>	<u>Results</u>	<u>AAMA 2604-02 Specification Requirements</u>
7.6 Abrasion Resistance	Pass (ACV = 42)	ACV 20 minimum
7.7 Chemical Resistance		
7.7.1 Muriatic Acid	Pass	No Blistering or Visible Change
7.7.2 Mortar	Pass	No Blistering or Visible Change
7.7.3 Nitric Acid	Pass ($\Delta E = 0.04$)	Hunter, Delta E = 5 max.
7.7.4 Detergent	Pass	No Film Adhesion Loss or Visible Change
7.7.5 Window Cleaner Resistance	Pass	No Blistering or Noticeable Change In Appearance and No Film Loss
7.8 Corrosion Resistance		
7.8.1 Humidity	Pass (No blisters)	Not Greater Than Few & No. 8 blisters
7.8.2 Salt Spray	Pass	
Scribe	9	7 Minimum Rating
Field	9	8 Minimum Rating

Date Testing Started: 8-19-04
 Date Testing Completed: 4-7-05
 Date Test Report Expires: N/A

Testing Conducted At: Dallas Laboratories, Inc., 1323 Wall Street, Dallas, Texas 75215.

The test results indicate that sample tested is in compliance with all of the performance requirements of AAMA 2604-02 for High Performance Organic Coatings on Aluminum Extrusions and Panels, except for Section 7.9 Weathering which must be furnished by the coating supplier for full compliance to AAMA 2604 as specified by AAMA.

DALLAS LABORATORIES, INC.



Kevan W. Jones, Vice President

Analyst: GF
 KWJ:td



REPORT

issued by an Accredited Testing Laboratory

Contact person
Maria Rådemar
Chemistry and Materials Technology
+46 10 516 51 65
maria.rademar@sp.se

Date
2011-11-18

Reference
FX118486-2

Page
1 (3)



Akzo Nobel Powder Coatings
Roger Strömvall
c/o International Färg AB
Box 44
424 22 ANGERED

Emission measurement after 4 weeks

(1 appendix)

Object

One sample of a lacquer was supplied to SP by the client. The lacquer arrived applied on stainless steel plates.

Sample marking:

Interpon D2525
lacquered 2011-10-05 by client
60 – 110 µm
25 x 25 cm, 2 plates

Date of arrival:

2011-10-11

Work requested

Emission measurements regarding volatile organic compounds (VOC) including carcinogenic substances (VOC-substances according to EU Directive 67/548/EEC kategori 1 and 2) and formaldehyde.

Methods

The emission was measured according to SS-EN ISO 16000-10:2006 "Indoor air – Part 10: Determination of the emission of volatile organic compounds from building products and furnishing – Emission test cell method", but only 28 days after application.

Tenax TA was used as adsorption medium for VOC. The Tenax tubes were thermally desorbed and analysed in accordance to ISO 16000-6:2004 (Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA sorbent, thermal desorption and gas chromatography using MS/FID), accredited SP method 0601. This means an analysis in a gas chromatograph and detection with a flame ionisation detector (FID) and mass selective detector (MS). The FID signals are used for compound quantification. The total volatile organic compounds (TVOC) means compounds eluting between and including n-hexane to octadecane, having boiling points in the range of about 70-320 °C. The TVOC is quantified in toluene equivalents and includes all compounds $ca \geq 1 \mu\text{g}/\text{m}^3$. The mass selective detector is used for identification of single compounds, quantified in compound specific amounts when possible, otherwise in toluene equivalents. Quantification limit for carcinogenic substances is $0.5 \mu\text{g}/\text{m}^2\text{h}$.

The sampling of formaldehyde was carried out with DNPH samplers. The analysis of the samplers were carried out according to ISO 16000-3:2001 "Indoor air--Part 3:Determination of

SP Technical Research Institute of Sweden

Postadress
SP
Box 857
SE-501 15 BORÅS
Sweden

Besöksadress
Västeråsen
Brinellgatan 4
SE-504 62 BORÅS

Tfn / Fax / E-post
+46 10 516 50 00
+46 33 13 55 02
info@sp.se

Laboratorier ackrediteras av Styrelsen för ackreditering och teknisk kontroll (SWEDAC) enligt svensk lag. Denna rapport får endast återges i sin helhet, om inte utfärdande laboratorium i förväg skriftligen godkänt annat.

formaldehyde and other carbonyl compounds – Active sampling method”, accredited SP method 2302. This means analysis on a liquid chromatograph with absorbance detector.

The specimens were stored for 22 days in a room with controlled climate conditions of 23 ± 2 °C and 50 ± 5 % RH. One of the test specimens was put into the test cell 24 h prior to air samplings of VOC and formaldehyde. Air samplings were carried out at 2011-11-03.

Conditions of the test in the FLEC cell:

Test chamber volume	0.000035 m ³
Area of sample	0.0177 m ²
Air change rate	171 h ⁻¹
Area specific air change rate	0.34 m ³ /m ² h
Temperature	23 ± 1 °C
Relative Humidity	50 ± 5 % RH

Results

The results are expressed as area specific emission rates:

$$SER_A = \frac{Conc \times n}{L}$$

SER_a = area specific emission rate, in µg/m²h
 Conc = concentration of a VOC in the test cell, in µg/m³
 n = air exchange rate, in changes per hour
 L = loading factor, in m²/m³ (area of sample/volume of test cell)

Interpon D2525:

Volatile organic compounds	Retention time (min)	CAS number	ID ¹	Emission rate (µg/m ² h)
TVOC (C₆ – C₁₆)	5.0 - 36.0	--	B	< 10
Identified substances:				
No substances identified	--	--	--	< 2
Carcinogenic substances²				
No substances identified	--	--	--	< 0.5
Substances outside VOC (C₆ – C₁₆):				
∑VVOOC (< C₆)³	3.5 – 5.0	--	B	< 10
No substances identified	--	--	--	--
∑SVOC (C₁₆ – C₂₂)⁴	36.0 - 42.0	--	B	< 10
No substances identified	--	--	--	--
Formaldehyde	--	50-00-0	A	< 2

¹⁾ ID: A = identified compound specific, B = identified as toluene-equivalent



- 2) VOC-substances, according to EU Directive 67/548/EEC categories 1 and 2
3) \sum VVOC = the sum of very volatile organic compounds, as defined in ISO 16000-6
4) \sum SVOC = the sum of semi-volatile organic compounds, as defined in ISO 16000-6

Quantification limit for TVOC is 10 $\mu\text{g}/\text{m}^3\text{h}$. Only VOC-compounds with a concentration higher than 2 $\mu\text{g}/\text{m}^3\text{h}$ are listed in the table (carcinogenic compounds > 0.5 $\mu\text{g}/\text{m}^3\text{h}$). Measurement uncertainty for VOC is 15 % (rel) and for formaldehyde 30 % (rel).

See Appendix 1 for gas chromatogram (FID spectra).

Summary

The amount of total volatile organic compounds (TVOC) was below quantification limit, that is very low emission.

No single substance was identified, they were all less than 0.5 $\mu\text{g}/\text{m}^3\text{h}$.

SP Technical Research Institute of Sweden Chemistry and Materials Technology - Organic Analytical Chemistry

Performed by

Examined by

Maria Rådemar

Marcus Vestergren

Appendix

1. Gas Chromatogram




Appendix I

Gas Chromatogram

Interpon D2525:

Abundance



Compound with retention time 3.9 min is a contamination from analysis system.



This is to certify that

Akzo Nobel UAE Paints L.L.C

*Supports the promotion and development of Sustainable Buildings
in the United Arab Emirates, and is a*


Corporate Member

of the

**مجلس الامارات للابنية الخضراء
Emirates Green Building Council**


Saeed Al Abbar
Chairman

January 2017 – December 2017


Habiba Al Marashi
Founder, Vice-Chairman & Treasurer

증서번호 : 82085918
 CERTIFICATE NO
 발급일 : 2019. 10. 10
 DATE OF ISSUE
 계약번호 : FF1901040
 CONTRACT NO

품명 : GALVANNEAL STEEL SHEET IN COILS
 COMMODITY
 사양규격 : ASTM A 853-98 CS TYPF A
 SPECIFICATION

고객 : B IN GHURAIR
 CUSTOMER
 취급사 : (주) 예스티인터내셔널
 SHIPPER
 목적지 : JFREI AI I
 DESTINATION

검사증명서
 INSPECTION CERTIFICATE

동부제철
 DONGBU STEEL CO., LTD.
 * HEAD OFFICE: 7F, Seoul Square, 416,
 Hangang-daero, Jung-gu,
 Seoul, Korea, 04637
 TEL: (02) 3450-8114
 E-MAIL: dbstcc@dongbu.com
 * Dangjin Works/ Cold Rolling Mill
 : 1228, Bukbusanep-ro, Songpak-eup,
 Dangjin-si, Chungcheongnam-do, KOREA
 TEL: (041) 351-8313

ORIGINAL

주문치수 ORDER SIZE	제품번호 PRODUCT NO		수량 QUANTITY	제품치수 DIMENSION(mm)		인장시험 TENSILE TEST		중도 THICKNESS	HR30T	결구 GRAIN	인장시험 TENSILE TEST	벤드시험 BEND TEST	스킨패스 SKIN PASS	CHEMICAL COMPOSITION(%)	비고 REMARKS
	검사번호 INSPECTION NO	CHARGE NO		두께 THICKNESS	나비 WIDTH	항복강도 Y.P	인장강도 T.S								
06 A40 SIZE TOTAL	5		20,463	45,106											
04 A40 1.500MM X 1500.0MM X C	1 IA0M7A	CZNS4350	4,170	9,193	1,500	1500.0	303.0	370.7	37.20.0000	57		G	Y	44	5 2 21 36 1
	3 IA0M2B	CZNS4350	4,170	9,193	1,500	1500.0	303.0	370.7	37.20.0000	57		G	Y	44	5 2 21 36 1
	4 IA0M7E	CZNS4350	4,140	9,127	1,500	1500.0	303.0	370.7	37.20.0000	57		G	Y	44	5 2 21 36 1
	5 IA0M2D	CZNS4350	4,160	9,171	1,500	1500.0	303.0	370.7	37.20.0000	57		G	Y	44	5 2 21 36 1
	10 IA0M2J	CZNS4350	2,830	8,444	1,500	1500.0	303.0	370.7	37.20.0000	57		G	Y	44	5 2 21 36 1
07 A40 SIZE TOTAL	5		20,470	45,128											
07 A40 2.000MM X 1220.0MM X C	1 HLB4AA	KYP23270	4,270	9,414	2,000	1220.0	298.3	354.0	35.00.0000	55		G	Y	30	14 7 1 18 39 1
	2 HLB4AC	KYP23270	4,270	9,414	2,000	1220.0	298.3	354.0	35.00.0000	55		G	Y	30	14 7 1 18 39 1
	3 HLB4AB	KYP23270	4,250	9,370	2,000	1220.0	298.3	354.0	35.00.0000	55		G	Y	30	14 7 1 18 39 1
	5 HLB4AD	KYP23270	4,270	9,414	2,000	1220.0	298.3	354.0	35.00.0000	55		G	Y	30	14 7 1 18 39 1
SIZE TOTAL	4		17,060	37,612											
FILE TOTAL	35		145,410	320,572											

* OIL TREATMENT
 U : UNILED (DRY)
 H : HEAVY OILED
 N : NORMAL OILED
 L : LIGHTLY OILED
 S : SLIGHTLY OILED
 B : BIG HEAVY OILED

* CHEMICAL TREATMENT
 N : NO CHROMIATED
 H : HEAVY CHROMIATED
 C : NORMAL CHROMIATED
 I : ITW CHROMIATED

* G : GOOD
 * ORGANIC
 V : YES
 N : NO
 O : Non-Cr Post Treatment
 B : B10 C07

상기 제품의 규격의 시험을 위하여 합격하였음을 증명합니다.
 WE HEREBY CERTIFY THAT THE PRODUCT DESCRIBED
 HEREIN HAS BEEN SATISFACTORILY TESTED IN
 ACCORDANCE WITH THE SPECIFICATION.

출력일시 : 2019.01.10 14:42 / 출력회사 : 1 회

CHIEF OF QUALITY ASSURANCE TEAM
 원본 - ORIGINAL

MADE IN KOREA

증명서 번호 : 82085918
 CERTIFICATE NO
 발급년월일 : JAN.10.2019
 DATE OF ISSUE
 계약번호 : EE1901040
 CONTRACT NO

품명 : GALVANNEALED STEEL SHEET IN COILS
 COMMODITY
 직용규격 : ASTM A 659-96 CS TYPE A
 SPECIFICATION

검사 증명서
 INSPECTION CERTIFICATE

동부제철
 DONGBU STEEL CO., LTD.

* HEAD OFFICE: 7F, Seoul Square, 416,
 Hangang-daero, Jung gu,
 Seoul, Korea, 04637

TEL : (02) 3450-8114

E-MAIL : dbsteel@dongbu.com

* Dangjin Works, Cold Rolling Mill

: 1228, Bukbusaneop-ro, Songpak-eup,

Dangjin-si, Chungcheongnam-do, KOREA

TEL : (041) 351-8313

ORIGINAL

고객 : BIN GHURAIR
 CUSTOMER

취급상사 : (주) 에스티인터내셔널
 SHIPPER

DESTINATION : JEBEL ALI

주문처수 ORDER SIZE	포장번호 PACK-AGE NO	검사번호 INSPECTION NO	제품번호 CHARGE NO	수량 QUANTITY		제품치수 DIMENSION(mm)			인장시험 TENSILE TEST			결단 HR30T	조도 ROUGHNESS	IMPACT TEST	BEND TEST	SKIN TEST	SKEW TEST	CUTTING TEST	OTDR COATING WEIGHT (g/m ²)	화학성분 CHEMICAL COMPOSITION(%)						비고 REMARKS				
				KGS	LBS	두께 THICKNESS	나비 WIDTH	길이 LENGTH	항복강도 Y.P	인장강도 T.S	연신율 EL.									R	C	P	S	SI	Mn		So	TI		
																													%	X 1000
02 1.200MM X 1050.0MM X C	1	HL8GSA	KZN43970	4,540	10,009	1,200	1050.0	001L	307.9	374.6	36.20.0000	59		G	G	Y	C	N	U	125.2	33	14	5	1	19	38	1			
	3	HL8GSB	KZN43970	4,560	10,031	1,200	1050.0	001L	307.9	374.6	36.20.0000	59		G	G	Y	C	N	U	125.2	33	14	5	1	19	38	1			
	5	HL8GSD	KZN43970	4,530	9,955	1,200	1050.0	001L	307.9	374.6	36.20.0000	59		G	G	Y	C	N	U	125.2	33	14	5	1	19	38	1			
	8	HL8GSH	KZN43970	4,260	9,382	1,200	1050.0	001L	307.9	374.6	36.20.0000	59		G	G	Y	C	N	U	125.2	33	14	5	1	19	38	1			
== SIZE TOTAL ==	4			17,870	39,397																									
05 1.200MM X 1220.0MM X C	1	HL7FJA	KYP23180	4,350	9,590	1,200	1220.0	001L	297.3	356.0	36.70.0000	56		G	G	Y	C	N	U	122.2	35	13	6	1	19	40	1			
	2	HL7FJC	KYP23180	4,350	9,590	1,200	1220.0	001L	297.3	356.0	36.70.0000	56		G	G	Y	C	N	U	122.2	35	13	6	1	19	40	1			
	3	HL7FJB	KYP23180	4,350	9,590	1,200	1220.0	001L	297.3	356.0	36.70.0000	56		G	G	Y	C	N	U	122.2	35	13	6	1	19	40	1			
	4	HL7FE	KYP23180	4,140	9,127	1,200	1220.0	001L	297.3	356.0	36.70.0000	56		G	G	Y	C	N	U	122.2	35	13	6	1	19	40	1			
	5	HL7FD	KYP23180	4,360	9,612	1,200	1220.0	001L	297.3	356.0	36.70.0000	56		G	G	Y	C	N	U	122.2	35	13	6	1	19	40	1			
== SIZE TOTAL ==	6			3,830	8,444	1,200	1220.0	001L	297.3	356.0	36.70.0000	56		G	G	Y	C	N	U	122.2	35	13	6	1	19	40	1			
03 1.200MM X 1500.0MM X C	6	IA0MXAB	CZN56680	4,110	9,061	1,200	1500.0	001L	298.1	371.7	37.00.0000	56		G	G	Y	C	N	U	122.3	44	14	5	2	21	35	1			
	7	IA0MXAA	CZN56680	4,110	9,061	1,200	1500.0	001L	298.1	371.7	37.00.0000	56		G	G	Y	C	N	U	122.3	44	14	5	2	21	35	1			
	8	IA0MXAD	CZN56680	4,110	9,061	1,200	1500.0	001L	298.1	371.7	37.00.0000	56		G	G	Y	C	N	U	122.3	44	14	5	2	21	35	1			

성기 제품은 규격의 시험을 행하여 합격하였음을 증명합니다.
 WE HEREBY CERTIFY THAT THE PRODUCT DESCRIBED
 HEREIN HAS BEEN SATISFACTORILY TESTED IN
 ACCORDANCE WITH THE SPECIFICATION.

출력일시 : 2019.01.10 14:42 / 출력횟수 : 1 회

* G : GOOD
 * ORGANIC
 Y : Yes
 N : No
 O : Non-Cr Post Treatment
 B : BIO COAT
 * CHEMICAL TREATMENT
 N : NO CHROMIATED
 H : HEAVY CHROMIATED
 C : NORMAL CHROMIATED
 L : LOW CHROMIATED
 * OIL TREATMENT
 U : UNOILED (DRY)
 H : HEAVY OILED
 N : NORMAL OILED
 L : LIGHTLY OILED
 S : SLIGHTLY OILED
 B : BIG HEAVY OILED

CHIEF OF QUALITY ASSURANCE TEAM
 원본 - ORIGINAL

MADE IN KOREA

증서번호 : 82085918
 CERTIFICATE NO : 82085918
 발급년월일 : JAN.10.2019
 DATE OF ISSUE : JAN.10.2019
 계약번호 : EE1901040
 CONTRACT NO : EE1901040

품명 : GALVANNEALED STEEL SHEET IN COILS
 COMMODITY : GALVANNEALED STEEL SHEET IN COILS
 적용규격 : ASTM A 653-96 CS TYPE A
 SPECIFICATION : ASTM A 653-96 CS TYPE A

검사증명서
 INSPECTION CERTIFICATE

ORIGINAL

고객 : BIN GHURAIR
 CUSTOMER : BIN GHURAIR
 취급상사 : (주) 에스티인터내셔널
 SHIPPER : (주) 에스티인터내셔널
 목적지 : JEBEL ALI
 DESTINATION : JEBEL ALI

동부제철
 DONGBU STEEL CO., LTD.
 * HEAD OFFICE: 7F, Seoul Square, 416,
 Hangang-daero, Jung-gu,
 Seoul, Korea, 04637
 TEL: (02) 3450-8114
 E-MAIL: dbsteel@dongbu.com
 * Dangjin Works/Coil Rolling Mill
 : 1228, Bukbusaneop-ro, Songak-eup,
 Dangjin-si, Chungcheongnam-do, KOREA
 TEL: (041) 351-8313

주요사항 ORDER SIZE	제품번호 PRODUCT NO	수량 QUANTITY	제품치수 DIMENSION(mm)		인장시험 TENSILE TEST	결단 HR30T	조각 TEST	IMPACT TEST	BEND TEST	SKIN PASS	CHEMICAL COMPOSITION(%)	REMARKS
			두께 THICKNESS	나비 WIDTH								
03 A40	9 1A0MXAC CZN56680	4,110	1,200	1500.0	371.7	37.0	56	G	G	Y	C	123.3
01 A40	12 1A0MXAEB CZN56680	3,860	1,200	1500.0	371.7	37.0	56	G	G	Y	C	123.3
06 A40	1 1A1GKA 80H90186	4,200	1,500	1220.0	343.2	40.9	54	G	G	Y	C	124.7
	2 1A1GKC 80H90186	4,200	1,500	1220.0	343.2	40.9	54	G	G	Y	C	124.7
	3 1A1GKB 80H90186	4,200	1,500	1220.0	343.2	40.9	54	G	G	Y	C	124.7
	4 1A1GKE 80H90186	4,110	1,500	1220.0	343.2	40.9	54	G	G	Y	C	124.7
	10 1A1GKJ 80H90186	3,750	1,500	1220.0	343.2	40.9	54	G	G	Y	C	124.7
* G : GOOD * ORGANIC Y : Yes N : No O : Non-Cr Post Treatment B : BIG CUT * CHEMICAL TREATMENT H : NO CHROMIATED C : NORMAL CHROMIATED L : LOW CHROMIATED * OIL TREATMENT U : UNOILED (DRY) H : HEAVY OILED N : NORMAL OILED L : LIGHTLY OILED S : SLIGHTLY OILED B : BIG HEAVY OILED												

확인

확인

확인

확인

확인

확인

확인

확인

출력일시 : 2019.01.10 14:42 / 출력횟수 : 1 회
 MADE IN KOREA
 CHIEF OF QUALITY ASSURANCE TEAM
 원본 - ORIGINAL

증서번호 : 82085918
 CERTIFICATE NO
 발급년월일 : JAN. 10. 2019
 DATE OF ISSUE
 계약번호 : FF1901040
 CONTRACT NO

품명 : GALVANNEALD STEEL SHEET IN COILS
 COMMODITY
 적용규격 : ASTM A 555-96 CS TYPF A
 SPECIFICATION

고객 : B.N GHURAIR
 CUSTOMER
 취급회사 : (주) 에스티인터내셔널
 SHIPPER
 DESTINATION : JFRF1 AI1

검사증명서
 INSPECTION CERTIFICATE

동부제철
 DONGBU STEEL CO., LTD.

별첨공정
 * HEAD OFFICE: Seoul Square, 416,
 Hangang-daero, Jung-gu,
 Seoul, Korea, 04637
 TEL : (02) 3450-8114
 E-MAIL : dbstcc@dongbu.com
 * Dangjin Works/Cold Rolling Mill
 : 1228, Bukbusanep-ro, Songpak-eup,
 Dangjin-si, Chungcheongnam-do, KOREA
 TEL : (041) 351-8313



주문치수 ORDER SIZE	제품번호 PRODUCT NO	수량 QUANTITY	제품치수 DIMENSION(mm)		인장시험 TENSILE TEST		경도 HARDNESS	종단 IMPACT TEST	BUNDT TEST	SKIN PASS	CHEMICAL COMPOSITION(%)	부착량 COATING WEIGHT (g/m ²)	비고 REMARKS
			두께 THICKNESS	나비 WIDTH	항복 강도 Y.P	인장 강도 T.S							
06 A4D SIZE TOTAL	5	20.463	4.081	45.106									
06 A4D 1.500MM X 1500.0MM X C	1 IAGMZA 3 IAGMZB 4 IAGMZE 5 IAGMZD 10 IAGMZJ	4.170 4.170 4.140 4.160 3.830	774 774 771 774 712	9.193 9.103 9.127 9.171 8.444	001L 001L 001L 001L 001L	333.0 333.0 333.0 333.0 333.0	370.7 370.7 370.7 370.7 370.7	37.20.0000 37.20.0000 37.20.0000 37.20.0000 37.20.0000	57 57 57 57 57	G G G G G	Y Y Y Y Y	122.4 122.4 122.4 122.4 122.4	1 1 1 1 1
07 A4D 2.000MM X 1220.0MM X C	1 HL84AA 2 HL84AC 3 HL84AB 5 HL84AD	4.270 4.270 4.250 4.270	732 732 728 732	9.414 9.414 9.370 9.414	001L 001L 001L 001L	298.3 298.3 298.3 298.3	354.0 354.0 354.0 354.0	35.00.0000 35.00.0000 35.00.0000 35.00.0000	55 55 55 55	G G G G	Y Y Y Y	125.1 125.1 125.1 125.1	1 1 1 1
SIZE TOTAL	4	17.060	2.924	37.612									
FILE TOTAL	35	145.410	38.133	320.572									

확인
 CHIEF OF QUALITY ASSURANCE TEAM
 원본 - ORIGINAL

* CHEMICAL TREATMENT
 N : NO OIL TREATMENT
 I : HEAVY OILED
 C : NORMAL OIL TREATED
 L : LIGHTLY OILED
 S : SLOTTED OILED
 B : BIG HEAVY OILED

* OIL TREATMENT
 U : UNOILED (DRY)
 I : HEAVY OILED
 N : NORMAL OILED
 L : LIGHTLY OILED
 S : SLOTTED OILED
 B : BIG HEAVY OILED

증명서 번호 : 82085918
 CERTIFICATE NO : 82085918
 발급년월일 : JAN.10.2019
 DATE OF ISSUE : JAN.10.2019
 계약번호 : EE1901040
 CONTRACT NO : EE1901040

품명 : GALVANNEALED STEEL SHEET IN COILS
 COMMODITY : GALVANNEALED STEEL SHEET IN COILS
 적용규격 : ASTM A 653-96 CS TYPE A
 SPECIFICATION : ASTM A 653-96 CS TYPE A

검사 증명서
 INSPECTION CERTIFICATE

동부제철 냉연공장
 DONGBU STEEL CO., LTD.

* HEAD OFFICE: 7F, Seoul Square, 416,
 Hangang-daero, Jung-gu,
 Seoul, Korea, 04637

TEL: (02) 3450-8114
 E-MAIL: dbsteel@dongbu.com

* Dangjin Works/Cold Rolling Mill
 : 1228, Bukbusaneop-ro, Songak-eup,
 Dangjin-si, Chungcheongnam-do, KOREA
 TEL: (041) 351-8313

고객 : BIN GHURAIR
 CUSTOMER : BIN GHURAIR

취급상사 : (주) 에스티인터내셔널
 SHIPPER : (주) 에스티인터내셔널

DESTINATION : JEBEL ALI



주문치수 ORDER SIZE	제품번호 PRODUCT NO		수량 QUANTITY		제품치수 DIMENSION(mm)			인장시험 TENSILE TEST			경도 HARDNESS	조각 FITNESS	IMPACT TEST	BEND TEST	SKIN PASS	CHEMICAL ELEMENT	부착량 COATING WEIGHT (g/m ²)	화학성분 CHEMICAL COMPOSITION(%)	비고 REMARKS		
	포장 PACK-AGE NO	검사번호 INSPECTION NO	CHARGE NO	매수 SHEET	COIL LENGTH (m, ft)	두께 THICK- NESS	나비 WIDTH	길이 LENGTH	항복 점 Y.P	인장 강도 T.S										연신 율 EL.	HR30T
	35			38,133	145,410	320,572															
GRAND TOTAL																					

상기 제품은 규격의 시험을 행하여 합격하였음을 증명합니다.
 WE HEREBY CERTIFY THAT THE PRODUCT DESCRIBED
 HEREIN HAS BEEN SATISFACTORILY TESTED IN
 ACCORDANCE WITH THE SPECIFICATION.

출력일시 : 2019.01.10 14:42 / 출력횟수 : 1 회

- * G : GOOD
- * ORGANIC
Y : Yes
N : No
- * CHEMICAL TREATMENT
N : NO OROMATED
H : HEAVY OROMATED
C : NORMAL OROMATED
L : LOW OROMATED
- * OIL TREATMENT
U : UNOILED (DRY)
H : HEAVY OILED
N : NORMAL OILED
L : LIGHTLY OILED
S : SLIGHTLY OILED
B : BIG HEAVY OILED

확인
 CHIEF OF QUALITY ASSURANCE TEAM
 원본 - ORIGINAL



فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold

Quality Plan.



الشرق الأوسط للعوازل ذ.م.م.
Middle East Insulation LLC
Quality Cladding Systems



بن غوير التجارية ذ.م.م.
Bin Ghurair Trading LLC



QUALITY POLICY

- To maintain a leading position in the quality of products in company scope.
- To meet the national/ international standards , codes/legal requirements
- To achieve continual improvement in products and services by setting quality objectives.
- To meet our customer satisfaction.





الشرق الأوسط للعوازل ذ.م.م.
Middle East Insulation LLC
Quality Cladding Systems



بن غريو التجارية ذ.م.م.
Bin Ghurair Trading LLC



QUALITY MANAGEMENT MANUAL

Quality Objectives:

The overall objective of the organization is continuous growth improved business. We understand this can be achieved only if we succeed to meet customer requirements. In order to achieve this primary objective, quality objectives are established at relevant functions. Whenever possible & required, the management has defined measurable objectives to evaluate the system performance at defined intervals. Some of the functional objectives are listed below whereas the other objectives are defined during various management review meetings.

Management Representative:

- ✓ Plan and execute at least one round of internal quality audits every six months to identify the weakness in procedures and processes.
- ✓ Provide quality system awareness training to all new employees.
- ✓ Provide quality improvement proposal during every management review meeting.
- ✓ Review and log all customer feedback and customer complaints, prepare the statistical summary on every six months and report to the Group Director/GM about the trend for effective improvement actions.

Customer related process (Sales):

- ✓ Sales Manager & Sales Engineers from MEI, BGT and RESOLCO are primary responsible for this operation and the objectives:
- ✓ Improve the business @ 10% every year in overall sales or every section like CLADDING, BAAB, EPS, RESOLCO & BGT doors.
- ✓ Develop the business to new heights and technologies, which have wide scope in the market.
- ✓ Measure customer satisfaction and action for improvements.

Purchasing:

- ✓ Re-evaluate all suppliers to monitor the supplier's performance within acceptable limits.
- ✓ Review the purchasing documents to understand the frequently purchased consumables and hence to establish minimum stock level. (To avoid the wastages of resources spend on frequent purchase, inspection and transportation.)

Finance & Account:

- ✓ Perform the project costing for all projects and prepare the statistical report to identify the weakness in estimation.
- ✓ Prepare the database for potential customers, who settle payments within the stipulated time frame.
- ✓ Settle payment to suppliers on time.

Production:

- ✓ Review all production non-conformances (minor / major) reported during inspection as well as customer complaints to decide upon the process improvements and training requirements of operations staff.

Quality Control:

- ✓ Analyze the various wastages, set targets for the reduction of wastes.
- ✓ Analyze the data of rejections/ failures in final inspection or client inspections on annual basis and define better controls over in process inspection.
- ✓ Quality Objectives has been established for the departments/sections such as Planning, Production, Quality, Sales, Purchase, Stores, Technical, Projects, Dispatch, Administration and Maintenance and is under the control of MR.



فالكون باور العالمية
Falcon Power Global
For Safety Equipment



Falcon Gold

ISO Certificate.

CERTIFICATE AWARDED TO



BIN GHURAIR METAL INDUSTRIES L.L.C

at

P.O.BOX NO: 55686, OFFICE NO: 597-400, BIN GHURAIR, DIP 2, DUBAI, UAE

Quality Registrar Systems certify that the management system of the above organization has been audited and found to be in compliance with the QRS requirements for registration of the management system standard detailed below:

ISO 9001:2015

Quality Management Systems

Scope of work

MANUFACTURING AND INSTALLATION OF FIRE RATED STEEL DOORS

EA 17

Certificate No: DQU-10724

Originally Registered: 15 MAR 2017

Latest Issue: 25 MAR 2021

Valid up-to: 14 MAR 2023


Quality Registrar Systems



MANAGING OFFICE ADDRESS:

Quality Registrar Systems
P.O. Box :26826
United Arab Emirates

Tel: +971-2-6714302

Fax: +971-2-6741449

www.qrsyst.com

WORLD WIDE CERTIFICATION

This certificate is the property of Quality Registrar Systems and remains valid subject to satisfactory annual surveillance audit. This certificate is only valid when confirmed by the Register listed in the Quality Registrar Systems (qrsyst.com)



Certificate Of Registration

Awarded to



QRS

بن غرير التجارية ذ.م.م.
Bin Ghurair Trading LLC

at

P.O. BOX NO: 55686, PLOT NO: 597-400, DUBAI INVESTMENT PARK -2, DUBAI, UAE

Quality Registrar Systems certify that the management system of the above organization has been audited and found to be in compliance with the QRS requirements for registration of the management system standard detailed below:

ISO 9001:2015

Quality Management Systems

Scope of work

TRADING OF FIRE RATED STEEL DOORS, SECTIONAL OVERHEAD DOORS, FIRE RATED ROLLING SHUTTERS, FOLDABLE DOORS, FIRE RATED ACCESS DOORS, SLIDING DOORS & RELATED IRONMONGERY

IAF 29

Certificate No: DQU-12398

Originally Registered: 05 DEC 2018

Latest Issue: 05 JAN 2022

Valid up-to: 04 DEC 2024

Quality Registrar Systems



MANAGING OFFICE ADDRESS:

Quality Registrar Systems
P.O. Box :26826
United Arab Emirates

Tel: +971-2-6714302
Fax: +971-2-6741449
www.qrsyst.com

WORLD WIDE CERTIFICATION

This certificate is the property of Quality Registrar Systems and remains valid subject to satisfactory annual surveillance audit.
This certificate is only valid when confirmed by the Register listed in the Quality Registrar Systems (qrsyst.com)



فالكون باور العالمية
Falcon Power Global
For Safety Equipment

اجعل السلامة
حقيقية



Falcon Power Global
For Safety Equipment



0547777503

٦١١٢ شارع فلسطين - جدة ٢٣٣٤١



Falcon Power Global